

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 130 132 A2**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

**05.09.2001 Bulletin 2001/36**

(51) Int Cl.7: **C23C 22/68**

(21) Application number: **01400522.7**

(22) Date of filing: **28.02.2001**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**

Designated Extension States:

**AL LT LV MK RO SI**

(30) Priority: **29.02.2000 JP 2000053010**

(71) Applicant: **NIPPON PAINT CO., LTD.**

**Kita-ku, Osaka-shi, Osaka 531 (JP)**

(72) Inventors:

- **Sasaki Motohiro**  
**Kanagawa 211-0063 (JP)**

• **Yamasoe Katsuyoski**

**Chiba 285-0807 (JP)**

• **Jung Christian**

**96173 Oberhaid (DE)**

• **The other inventors have agreed to waive their entitlement to designation.**

(74) Representative: **Hubert, Philippe et al**

**Cabinet Beau de Loménie**

**158, rue de l'Université**

**75340 Paris Cédex 07 (FR)**

(54) **Nonchromate metallic surface treating agent for PCM use, method for PCM surface treatment, and treated PCM steel panel**

(57) The present invention has for its object to provide a metallic surface treating agent for PCM use, which is capable of imparting high processability and corrosion resistance to PCM steel panels with the additional advantage of improved storage stability, a method for surface treatment of a PCM steel panel, a method of producing a PCM steel panel, and a PCM steel panel as produced by said method.

This invention provides a nonchromate metallic surface treating agent for PCM use

which comprises, in each liter thereof,

(a) a silane coupling agent and/or a hydrolytic condensation product thereof in an amount of 0.01 to 100 g/l,

(b) water-dispersible silica in a proportion of 0.05 to 100 g/l (solids), and

(c) a zirconium compound in an amount of 0.01 to 50 g/l in terms of zirconium ion and/or a titanium compound in an amount of 0.01 to 50 g/l in terms of titanium ion.

**EP 1 130 132 A2**

## Description

## FIELD OF THE INVENTION

5 [0001] The present invention relates to a metallic surface treating agent for metallic substrates, particularly precoated (hereinafter referred to briefly as PCM) steel panels for use as metal-coated steel plates such as the zinc-coated steel panel, aluminum-coated steel panel, tin-coated steel panel, etc., a method for surface treatment of a PCM steel panel, a method of producing a PCM steel panel, and a PCM steel panel as produced by said method.

## 10 PRIOR ART

[0002] As the metallic surface treating agent, a chromium-containing surface treating agent such as a chromate system or a phosphate-chromate system has heretofore been used broadly and still in use today. However, in view of the recent trend toward more stringent regulatory control for environmental protection, it is likely that the use of such coating systems will be restricted for fear of the toxicity, particularly carcinogenicity, of chromium. Therefore, development of a rust-preventing agent not containing chromium and yet as effective as the chromating agent in imparting corrosion resistance has been awaited. As disclosed in Japanese Kokai Publication Hei-11-29724, the inventors of the present invention previously developed a nonchromate rust-preventing agent comprising a water-base resin and, as incorporated therein, a thiocarbonyl group-containing compound, a phosphate ion, and water-dispersible silica. Regrettably, however, this system was found to be deficient in storage stability and somewhat poor in corrosion resistance at thin coating thickness. Meanwhile, with regard to silane coupling agents, an acidic surface treating agent containing two dissimilar silane coupling agents is disclosed in Japanese Kokai Publication Hei-8-73775. However, this system is intended to improve finger-print resistance and overcoat adhesion and is quite deficient in corrosion resistance for use in applications where high corrosion resistance and good processability are required after such metallic surface treatment as in the present invention. Moreover, Japanese Kokai Hei-10-60315 discloses a steel structure surface treating agent, which contains a silane coupling agent having a certain functional group reactive with an aqueous emulsion, but the corrosion resistance required here is only that of a degree satisfying comparatively mild test requirements such as those of wet tests and as far as corrosion resistance is concerned, the system does not meet the requirements of a rust-preventing agent system as provided by the present invention. With the above state of the art by way of background, there has been a standing demand for development of a rust-preventing agent expressing sufficient corrosion resistance and overcoat adhesion at thin coating thickness.

[0003] Meanwhile, in the field of PCM steel panels, too, the advent has been awaited of a PCM steel panel produced by using a nonchromate rust-preventing agent and yet expressing overcoat adhesion and corrosion resistance comparable or superior to those of the conventional chromated PCM steel panel.

## 35 SUMMARY OF THE INVENTION

[0004] The present invention has for its object to provide a nonchromate metallic surface treating agent for PCM use which is suited for metal-coated steel panels, particularly galvanized steel panels and is capable of imparting high processability and corrosion resistance to PCM steel panels, with the additional advantage of improved storage stability.

[0005] The nonchromate metallic surface treating agent for PCM use according to the present invention comprises, in each liter thereof,

- (a) a silane coupling agent and/or a hydrolytic condensation product thereof in an amount of 0.01 to 100 g/l,
- (b) water-dispersible silica in an amount of 0.05 to 100 g/l (solids), and
- (c) a zirconium compound in an amount of 0.01 to 50 g/l in terms of zirconium ion and/or a titanium compound in an amount of 0.01 to 50 g/l in terms of titanium ion.

[0006] The nonchromate metallic surface treating agent for PCM use according to the present invention may contain one or more members selected from among sulfide ion, thiosulfate ion, persulfate ion and a triazinethiol compound in an amount of 0.01 to 100 g/l.

[0007] The method of treating a metallic surface according to the present invention comprises treating the surface of a metal-coated steel panel with any of the above metallic surface treating agents, and is most suited for the surface treatment of zinc-coated steel panels.

[0008] The method of producing a PCM steel panel according to the present invention comprises treating the surface of a metal-coated steel panel with any of said metallic surface treating agents and applying a chromium-free primer and a top coating serially thereon.

[0009] The PCM steel panel of the present invention is obtainable by the above production method.

## DETAILED DESCRIPTION OF THE INVENTION

**[0010]** As the silane compound as one of its essential components, the metallic surface treating agent of the present invention contains a silane coupling agent and/or a hydrolytic condensation product thereof. The hydrolytic condensation product of a silane coupling agent means an oligomer obtainable by hydrolytic polymerization of the silane coupling agent.

**[0011]** The silane coupling agent which can be used as above in the present invention is not particularly restricted but includes the following, among others: vinylmethoxysilane, vinyltrimethoxysilane, vinylethoxysilane, vinyltriethoxysilane, 3-aminopropyltriethoxysilane, 3-glycidoxypropyltrimethoxysilane, 3-methacryloxypropyltrimethoxysilane, 3-mercaptopropyltrimethoxysilane, N-(1,3-dimethylbutylidene)-3-(triethoxysilyl)-1-propanamine, N,N'-bis[3-(trimethoxysilyl)propyl]ethylenediamine, N-( $\beta$ -aminoethyl)- $\gamma$ -aminopropylmethyldimethoxysilane, N-( $\beta$ -aminoethyl)- $\gamma$ -aminopropyltrimethoxysilane,  $\gamma$ -aminopropyltrimethoxysilane,  $\gamma$ -aminopropyltriethoxysilane,  $\gamma$ -glycidoxypropyltrimethoxysilane,  $\gamma$ -glycidoxypropylmethyldimethoxysilane, 2-(3,4-epoxycyclohexyl)ethyltrimethoxysilane,  $\gamma$ -methacryloxypropyltrimethoxysilane,  $\gamma$ -methacryloxypropyltriethoxysilane,  $\gamma$ -mercaptopropyltrimethoxysilane,  $\gamma$ -mercaptopropyltriethoxysilane and N-[2-(vinylbenzylamino)ethyl]-3-aminopropyltrimethoxysilane.

**[0012]** The particularly preferred silane coupling agent includes vinylmethoxysilane, vinylethoxysilane, 3-aminopropyltriethoxysilane, 3-glycidoxypropyltrimethoxysilane, 3-methacryloxypropyltrimethoxysilane, 3-mercaptopropyltrimethoxysilane, N-(1,3-dimethylbutylidene)-3-(triethoxysilyl)-1-propanamine and N,N'-bis[3-(trimethoxysilyl)propyl]ethylenediamine. These silane coupling agents can be used each alone or in a suitable combination.

**[0013]** In the present invention, said silane compound is caused to be present in a concentration of 0.01 to 100 g/l, preferably 0.5 to 25 g/l, in [each liter of] the metallic surface treating agent. If the concentration of the silane coupling compound is less than 0.01 g/l, the corrosion resistance- and adhesion-enhancing effect of the nonchromate rust-preventive coating agent will be deficient. If the use of the silane coupling compound exceeds 100 g/l, the corrosion resistance-enhancing effect will not be improved any further and rather an economic disadvantage will result.

**[0014]** With the silane compound as one of its essential components, the metallic surface treating agent of the present invention contains water-dispersible silica. The water-dispersible silica which can be used in the present invention is not particularly restricted but is preferably spherical silica, chainlike silica or aluminum-modified silica, which has a low content of sodium and other impurities and weakly basic. The spherical silica includes colloidal silicas such as "Snowtex N" and "Snowtex UP" (both manufactured by Nissan Chemical) and fumed silica such as "Aerosil" (Japan Aerosil); the chainlike silica includes silica gel such as "Snowtex PS" (Nissan Chemical); and the aluminum-modified silica includes "Adelite AT-20A" (Asahi Denka), all of which are commercially available.

**[0015]** The water-dispersible silica is caused to be present in an amount of 0.05 to 100 g/l, preferably 0.5 to 60 g/l, on a solid basis, in each liter of the metallic surface treating agent. If the proportion of water-dispersible silica is less than 0.05 g/l, the corrosion resistance-enhancing effect will be insufficient, while the use of silica in excess of 100 g/l will not be rewarded with any further improvement in corrosion resistance but rather detract from the bath stability of the metallic surface treating agent.

**[0016]** The metallic surface treating agent of the present invention further contains a zirconium compound and/or a titanium compound. The zirconium compound includes ammonium zirconyl carbonate, zirconium hydrofluoride, ammonium zirconium fluoride, potassium zirconium fluoride, sodium zirconium fluoride, zirconium acetylacetonate, zirconium butoxide-1-butanol solution, zirconium n-propoxide and so on. The titanium compound includes titanium hydrofluoride, ammonium titanium fluoride, potassium titanium oxalate, titanium isopropoxide, isopropyl titanate, titanium ethoxide, titanium 2-ethyl-1-hexanolate, tetraisopropyl titanate, tetra-n-butyl titanate, potassium titanium fluoride, sodium titanium fluoride, and so on. These compounds may be used each alone or in a suitable combination.

**[0017]** The above-mentioned zirconium compound and/or titanium compound is caused to be present, in each liter of the metallic surface treating agent of the invention, in a concentration of 0.01 to 50 g/l, preferably 0.05 to 5 g/l, in terms of zirconium ion or titanium ion. If the concentration of the above compound falls less than 0.01 g/l, corrosion resistance will become insufficient. If it exceeds 50 g/l, no improvement will be realized in overcoat adhesion and, in addition, the bath stability will be rather sacrificed.

**[0018]** The metallic surface treating agent of the present invention may further contain at least one sulfur-containing compound selected from the group consisting of a sulfide, a thiosulfuric acid compound, a persulfuric acid compound, and these compounds contribute to corrosion resistance.

**[0019]** The sulfide mentioned above includes sodium sulfide, ammonium sulfide, manganese sulfide, molybdenum sulfide, iron sulfide and vanadium sulfide, among others.

**[0020]** The thiosulfate includes ammonium thiosulfate, sodium thiosulfate and potassium thiosulfate, among others.

**[0021]** The persulfate includes ammonium persulfate, sodium persulfate and potassium persulfate, among others.

**[0022]** The triazinethiol compound includes 2,4,6-trimercapto-S-triazine, 2-butylamino-4,6-dimercapto-S-triazine, 2,4,6-trimercapto-S-triazine monosodium salt, 2,4,6-trimercapto-S-triazine trisodium salt, 2-anilino-4,6-dimercapto-S-triazine, and 2-anilino-4,6-dimercapto-S-triazine monosodium salt, among others.

[0023] These compounds can be used each alone or in a suitable combination.

[0024] The concentration of the above sulfur-containing compound(s) in the metallic surface treating agent, per liter of the composition, is 0.01 to 100 g/l, preferably 0.1 to 10 g/l, in terms of a total amount of sulfide ion, thiosulfate ion, persulfate ion and/or triazine compound. If the concentration of said ion(s) is less than 0.01 g/l, the expected corrosion resistance-enhancing effect will not be expressed. On the other hand, if the upper limit of 100 g/l is exceeded, the corrosion resistance-enhancing effect will not be improved any further and rather an economic disadvantage will result.

[0025] The metallic surface treating agent of the present invention may further contain other components. As such other components, there can be mentioned tannic acid inclusive of its salt, phytic acid inclusive of its salt, and water-base resin. The water-base resin which can be used includes acrylic resin, urethane resin, epoxy resin, ethylene-acrylic copolymer, phenolic resin, polyester resin and polyacrylic resin, among others. When a water-base resin is used, an organic solvent may be used concomitantly for improving its film-forming properties to thereby provide a more uniform, smooth film.

[0026] The metallic surface treating agent of the present invention can be used as a surface treating agent for metal-coated steel panels such as zinc-coated, aluminum-coated, tin-coated and other coated steel panels. The method of using this surface treating composition, that is to say the method of treating a metallic surface, may comprise applying said metallic surface treating agent to a substrate metallic surface and drying the coat or comprise heating such a substrate in advance, applying the metallic surface treating agent of the invention and allowing the coat to dry by utilizing the residual heat of the substrate.

[0027] In both cases, the above drying procedure can be carried out at room temperature to 250 °C for 2 seconds to 5 minutes. If the limit of 250 °C is exceeded, adhesion and corrosion resistance will be adversely affected. The preferred conditions are 40 to 180 °C and 5 seconds to 2 minutes.

[0028] In the method of treating a metallic surface according to the present invention, the amount of deposition of said metallic surface treating agent of the invention is preferably not less than 0.1 mg/m<sup>2</sup> as a dry coat thickness. If the amount of deposition is less than 0.1 mg/m<sup>2</sup>, the rust-preventive effect will be insufficient. On the other hand, if the amount of deposition is excessive, it will be uneconomical as an under coat for PCM coating and, in addition, cumbersome procedure-wise. Therefore, the more preferred amount of deposition is 0.5 to 500 mg/m<sup>2</sup>, particularly 1 to 250 mg/m<sup>2</sup>.

[0029] In the method of treating a metallic surface according to the present invention, the mode of use of said metallic surface treating agent is not particularly restricted. Thus, the routine techniques such as roller coating, shower coating, spray coating, dipping and brush coating can be selectively employed. The optimum steel substrate includes metal-coated steel panels, particularly zinc-coated steel panels, for PCM use.

[0030] The method of producing PCM steel panels according to the present invention comprises treating a metal-coated steel panel with said metallic surface treating agent, drying the coat, applying a nonchromate primer, drying the primer coat, and finally applying a top coating.

[0031] Said nonchromate primer may be any primer not containing a chromate type rust-preventive pigment in its formation. Preferred primer is a primer containing a vanadate type rust-preventive pigment and a phosphate type rust-preventive pigment (V/P pigment primer).

[0032] The coating amount of said primer is preferably equivalent to a dry coat thickness of 1 to 20 µm. If the dry coat thickness is less than 1 µm, corrosion resistance will be insufficient. If the thickness exceeds 20 µm, overcoat adhesion will not be as good as desired. The curing conditions for said nonchromate primer may be 150 to 250 °C, in terms of metal surface temperature, and a curing time of 10 seconds to 5 minutes.

[0033] The top coating mentioned above is not particularly restricted but may be any of the conventional top coatings for PCM use.

[0034] The coating technology for said nonchromate primer and said top coating is not particularly restricted but includes roller coating, shower coating, air-spray coating, airless-spray coating and dip coating, among others.

[0035] The nonchromate metallic surface treating agent for PCM use according to the invention contains a silane coupling agent and/or a hydrolytic condensation product thereof, water-dispersible silica, and a zirconium compound and/or a titanium compound. This metallic surface treating agent is suited to metals, particularly zinc-coated steel panels, is capable of imparting excellent processability and corrosion resistance to PCM steel panels without enlisting the help of chromium, and exhibits a sufficiently long shelf-life.

[0036] Furthermore, by applying the metallic surface treating agent of the invention to a process for producing non-chromated PCM steel panels, steel panels can be provided with processability and corrosion resistance equivalent or even superior to those of the conventional PCM steel panels obtainable by using a chromate-containing rust-preventing agent.

[0037] The above advantages seem to come forth from the fact that as the metallic surface treating agent of the present invention contains a silane coupling agent, the reactive moiety of the silane coupling agent is firmly bound to the substrate metal surface through metasiloxane bonding and the organic moiety of the hydrophobic group is firmly bound to the organic nonchromate primer film coated thereon to improve adhesion and thereby contribute to increased

corrosion resistance. Moreover, particles of the water-dispersible silica are adsorbed and oriented on the substrate surface to act as a barrier against corrosive ions and moisture and thereby suppress corrosion, while the silanol group present on the silica surface enhances the adhesion between the organic primer coat formed thereon and the metal surface. As to the zirconium ion, the formation of a zirconium oxide coat on the metal surface enhances corrosion resistance and, at the same time, the zirconium acts as a crosslinking agent for the primer applied thereon to increase the crosslinking density of the organic film to thereby further contribute to corrosion resistance, adhesion and coin scratch resistance. In addition, the sulfur-containing compound passivates the metal surface, thus contributing to corrosion resistance.

**[0038]** The PCM steel panel obtained in accordance with the present invention has excellent processability and corrosion resistance and, as such, finds application in a broad field of uses, such as household electrical appliances, computer-related devices, architectural members, and automotive and other industrial products.

#### EXAMPLES

**[0039]** The following examples are intended to describe the present invention in further detail and should by no means be construed as defining the scope of the invention.

##### Example 1

**[0040]** To 1 l of pure water were added 1.5 g of Sila-Ace S-330 ( $\gamma$ -aminopropyltriethoxysilane; Chisso Corporation), and the mixture was stirred at room temperature for 5 minutes. Then, 0.5 g of Snowtex N (water-dispersible silica; Nissan Chemical) was further added and the mixture was stirred for 5 minutes. In addition, 0.02 g, in terms of Zr ion, of Zircosol AC-7 (zirconyl ammonium carbonate; Daiichi Rare Elements Co.) was added, followed by stirring for 5 minutes to give a nonchromate metallic surface treating agent for PCM use. This metallic surface treating agent was degreased with an alkaline cleaner (Surf Cleaner 155; Nippon Paint) and, using a #3 bar coater, applied onto a dried commercial zinc hot-dip galvanized steel plate (Nippon Test Panel Co.;  $70 \times 150 \times 0.4$  mm) in a dry film thickness equivalent to 20 mg/m<sup>2</sup>. After drying at a metal surface temperature of 60 °C, a V/P pigment-containing nonchromate primer was applied in a dry film thickness of 5  $\mu$ m using a #16 bar coater and dried at a metal surface temperature of 215 °C. Further, using a #36 bar coater, Flexicoat 1060 (a polyester top coating paint; Nippon Paint) was applied in a dry film thickness of 15  $\mu$ m as a top coating and dried at a metal surface temperature of 230 °C to prepare a testpiece. The bending adhesion, corrosion resistance, coin scratch resistance of the testpiece and the bath stability of the metallic surface treating agent were evaluated by the methods described hereinafter and the results were tabulated as shown in Table 1.

##### Examples 2 to 6 and Comparative Examples 1 and 2

**[0041]** Except that the silane coupling agent, water-dispersible silica and zirconium compound were varied in kind and concentration as shown in Table 1, the procedure of Example 1 was otherwise followed to prepare metallic surface treating agents. Using these metallic surface treating agents, testpieces were prepared in the same manner as in Example 1. These testpieces and the metallic surface treating agents (baths) were evaluated by the same methods as above. The results are shown in Table 1.

##### Comparative Example 3

**[0042]** Except that a commercial chromating agent for coating use (resin-containing type), in lieu of the metallic surface treating agent of the invention, was applied at a chromium deposition rate of 20 mg/m<sup>2</sup> and dried and that a chromate-containing primer (a primer containing a strontium chromate pigment) was used, the procedure of Example 1 was otherwise followed to prepare a testpiece and evaluate it. The results are shown in Table 1.

Table 1

No.	Coupling agent		Silica		Zr compound		Primer	Bending adhesion		Corrosion resistance		Coin scratch resistance	Bath stability
	Kind	g/L	Kind	g/L	Kind	g/L		Pri- mary	Sec- ondary	Cut zone	End face		
Example	1	1	1	0.5	1	0.02	Non-chromate	5	5	5	5	4	0
	2	2	1	2.5	1	0.5	Non-chromate	5	5	5	5	5	0
	3	2	1	10	1	0.07	Non-chromate	5	5	5	4	5	0
	4	2	1	0.02	1	90	Non-chromate	5	5	5	5	5	0
	5	1	1	90	2	0.1	Non-chromate	5	5	5	5	5	0
	6	3	2	5	3	10	Non-chromate	5	5	5	5	5	0
Compar. ex.	1	2	1	200	2	100	Non-chromate	1	1	4	3	2	x
	2	1	1	0.005	2	0.005	Non-chromate	2	1	2	2	1	0
	3	Chromating agent for coating use					Chromate	2	5	4	3	4	-

Examples 7 to 12

[0043] The silane coupling agent, water-dispersible silica, zirconium compound and sulfur-containing compound were varied in kind and concentration as shown in Table 2, the procedure of Example 1 was otherwise repeated to prepare metallic surface treating agents. Using these metallic surface treating agents, testpieces were prepared in the same manner as in Example 1. Except that the salt spray time for corrosion resistance evaluation was changed to 500 hours, these testpieces were evaluated as in Example 1. The results are shown in Table 2.

10

15

20

25

30

35

40

45

50

55

Table 2

No.	Coupling agent		Silica		Zr compound		S compound		Primer	Bending adhesion		Corrosion resistance		Coin scratch resistance	bath stability
	Kind	g/L	Kind	g/L	Kind	g/L	Kind	g/L		Pri- mary	Sec- ondary	Cut zone	Edge		
7	1	2.5	1	25	2	0.5	1	0.02	Non-chromate	5	5	5	5	5	0
8	2	25	1	5	1	5	2	75	Non-chromate	5	5	5	5	5	0
9	1	50	1	0.1	2	0.1	4	1	Non-chromate	5	5	5	5	5	0
10	2	5	1	1	1	0.2	3	5	Non-chromate	5	5	5	5	5	0
11	1	1.5	2	0.5	4	5	3	2.5	Non-chromate	5	5	5	5	5	0
12	2	2.5	1	1.5	5	0.5	3	1.5	Non-chromate	5	5	5	5	5	0
13	2	1.5	1	2.5	1+5	0.5+0.5	3	5	Non-chromate	5	5	5	5	5	0

**[0044]** As the silane coupling agent, water-dispersible silica, zirconium compound, titanium compound and sulfur-containing compound (S compound) indicated above in Tables 1 and 2, the following commercial products were used.

[Silane coupling agent]

- 1: Sila Ace S-330 ( $\gamma$ -aminopropyltriethoxysilane; Chisso Corporation)
- 2: Sila Ace S-510 ( $\gamma$ -glycidoxypyltrimethoxysilane; Chisso Corporation)
- 3: Sila Ace S-810 ( $\gamma$ -mercaptopropyltrimethoxysilane; Chisso Corporation)

[Water-dispersible silica]

- 1: Snowtex N (Nissan Chemical)
- 2: Snowtex O (Nissan Chemical)

[Zirconium compound]

- 1: Zircosol AC-7 (ammonium zirconyl carbonate (Daiichi Rare Elements))
- 2: Ammonium zirconium fluoride (reagent)
- 3: Zirconium hydrofluoride (reagent)

[Titanium compound]

- 1: Titanium hydrofluoride (reagent)
- 2: Ammonium titanium fluoride (reagent)

[Sulfur compound]

- 1: Ammonium sulfide (reagent)
- 2: Ammonium persulfate (reagent)
- 3: Ammonium thiosulfate (reagent)
- 4: Triazinethiol (Santhiol N-1; Sankyo Kasei Co.)

<Method of Evaluation>

**[0045]** In the above Examples 1 to 13 and Comparative Examples 1 to 3, bending adhesion, corrosion resistance, coin scratch resistance and bath stability were evaluated in accordance with the following methods and criteria.

Bending adhesion

(Primary adhesion)

**[0046]** The testpiece was bent by 180° (OTT) without interposition of a spacer in an environment controlled at 20 °C and the bent part was peeled 3 times using an adhesive tape. The degree of peeling was examined under a  $\times 20$  magnifying glass and rated on the following scale.

Score

**[0047]**

- 5 points: no cracks
- 4 points: cracks all over the bend
- 3 points: the peeled area is less than 20% of the bend
- 2 points: the peeled area is not less than 20% and less than 80% of the bend
- 1 point: the peeled area is over 80% of the bend

(Secondary adhesion)

**[0048]** The testpiece was immersed in boiling water for 2 hours and, then, allowed to sit under indoor conditions for

## EP 1 130 132 A2

24 hours. The testpiece thus treated was bent in the same manner and rated on the same scale as in the primary adhesion test.

### Corrosion resistance

(Cut zone)

[0049] The testpiece was cross-cut and subjected to the same salt spray test according to JIS Z 2317 for 360 hours (Examples 1 to 6; Comparative Examples 1 to 3) or 500 hours (Examples 7 to 13). The width of the blister formed on one side of the cutting line was measured and rated on the following scale.

### Score

#### [0050]

- 5 points: blister width = 0 mm
- 4 points: blister width < 1 mm
- 3 points: blister width  $\geq$  1 mm but < 3 mm
- 2 points: blister width  $\geq$  3 mm but < 5 mm
- 1 point: blister width  $\geq$  5 mm

(Edge)

[0051] The testpiece was subjected to a salt spray test as directed in JIS Z 2317 for 360 hours and the width of the blister formed along the upper burr edge was rated on the same scale as used for the cut zone.

### Coin scratch resistance

[0052] The testpiece was scratched under a load of 1 kg using a coin scratch tester and the injured part was evaluated on the following rating scale.

### Score

#### [0053]

- 5 points: exposed primer area < 10%; base metal not exposed
- 4 points: exposed primer area  $\geq$  10% but < 70%; base metal not exposed
- 3 points: exposed primer area  $\geq$  70%; exposed base metal area < 30%
- 2 points: exposed primer area  $\geq$  70%; exposed base metal area  $\geq$  30% but < 70%
- 1 point: exposed primer area  $\geq$  70%; exposed base metal area  $\geq$  70%

### Bath stability

[0054] The metallic surface treating agent was stored in an incubator at 40 °C for 30 days and the degree of gelation and precipitation was evaluated on the following rating scale.

- : Neither gelation nor precipitation found
- ×: Gelation or precipitation found

[0055] It can be seen from Tables 1 and 2 that the metallic surface treating agent of the present invention has a good shelf-life and that the nonchromate PCM steel panel produced by the method of the invention shows overcoat adhesion and corrosion resistance equivalent or superior to those of the chromated PCM steel panel.

### **Claims**

1. A nonchromate metallic surface treating agent for PCM use which comprises, in each liter thereof,

EP 1 130 132 A2

- (a) a silane coupling agent and/or a hydrolytic condensation product thereof in an amount of 0.01 to 100 g/l,  
(b) water-dispersible silica in an amount of 0.05 to 100 g/l (solids), and  
(c) a zirconium compound in an amount of 0.01 to 50 g/l in terms of zirconium ion and/or a titanium compound  
in an amount of 0.01 to 50 g/l in terms of titanium ion.

- 5
2. The nonchromate metallic surface treating agent for PCM use according to Claim 1  
containing one or more members selected from among sulfide ion, thiosulfate ion, persulfate ion and a tri-  
azinethiol compound in an amount of 0.01 to 100 g/l.
- 10
3. A method of treating a metallic surface  
which comprises treating a metal-coated steel panel with the metallic surface treating agent according to  
Claim 1 or 2.
- 15
4. The method of treating a metallic surface according to Claim 3  
wherein the metal-coated steel panel is a zinc-coated steel panel.
- 20
5. A method of producing a PCM steel panel  
which comprises treating the surface of a metal-coated steel panel with the metallic surface treating agent  
according to Claim 1 or 2 and applying a chromium-free primer and a top coating serially thereon.
- 25
- 30
- 35
- 40
- 45
- 50
- 55
6. A PCM steel panel as obtainable by the method according to Claim 5.

**THIS PAGE BLANK (USPTO)**

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 130 132 A3**

(12)

**EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:  
28.01.2004 Bulletin 2004/05

(51) Int Cl.7: **C23C 22/68, C23C 22/34**

(43) Date of publication A2:  
05.09.2001 Bulletin 2001/36

(21) Application number: **01400522.7**

(22) Date of filing: **28.02.2001**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

- **Yamasoe Katsuyoski**  
**Chiba 285-0807 (JP)**
- **Jung Christian**  
**96173 Oberhaid (DE)**
- **The other inventors have agreed to waive their entitlement to designation.**

(30) Priority: **29.02.2000 JP 2000053010**

(71) Applicant: **NIPPON PAINT CO., LTD.**  
**Kita-ku, Osaka-shi, Osaka 531 (JP)**

(74) Representative: **Hubert, Philippe et al**  
**Cabinet Beau de Loménie**  
**158, rue de l'Université**  
**75340 Paris Cédex 07 (FR)**

(72) Inventors:  
• **Sasaki Motohiro**  
**Kanagawa 211-0063 (JP)**

(54) **Nonchromate metallic surface treating agent for PCM use, method for PCM surface treatment, and treated PCM steel panel**

(57) The present invention has for its object to provide a metallic surface treating agent for PCM use, which is capable of imparting high processability and corrosion resistance to PCM steel panels with the additional advantage of improved storage stability, a method for surface treatment of a PCM steel panel, a method of producing a PCM steel panel, and a PCM steel panel as produced by said method.

This invention provides a nonchromate metallic surface treating agent for PCM use  
which comprises, in each liter thereof,

(a) a silane coupling agent and/or a hydrolytic con-

densation product thereof in an amount of 0.01 to 100 g/l,  
(b) water-dispersible silica in a proportion of 0.05 to 100 g/l (solids), and  
(c) a zirconium compound in an amount of 0.01 to 50 g/l in terms of zirconium ion and/or a titanium compound in an amount of 0.01 to 50 g/l in terms of titanium ion.

**EP 1 130 132 A3**



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 01 40 0522

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 358 338 A (ALCAN INT LTD) 14 March 1990 (1990-03-14) * examples 1-10,14 *	1	C23C22/68 C23C22/34
X	US 4 330 446 A (MIYOSAWA YOSHIAKI) 18 May 1982 (1982-05-18) * column 2, line 13 - column 3, line 12; claims * * column 6, line 10 - line 45 * * column 7, line 42 - line 46 *	1,3,4	
A	EP 0 878 519 A (NIPPON PAINT CO LTD ;NIPPON STEEL CORP (JP)) 18 November 1998 (1998-11-18) * page 6, line 31 - line 39; claims; example 1; table 1 * & JP 11 029724 A 2 February 1999 (1999-02-02)	1-6	
D,A			
A	DATABASE WPI Section Ch, Week 197931 Derwent Publications Ltd., London, GB; Class A82, AN 1979-56933B XP002263689 & JP 54 077635 A (KANSAI PAINT CO LTD), 21 June 1979 (1979-06-21) * abstract *	1-6	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C23C
A	EP 0 979 880 A (NIPPON PAINT CO LTD) 16 February 2000 (2000-02-16) * claims *	1-6	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 3 December 2003	Examiner Mauger; J
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (F04C01)

# ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 01 40 0522

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

03-12-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0358338	A	14-03-1990	AT 109217 T	15-08-1994
			AU 625900 B2	16-07-1992
			AU 3951189 A	15-02-1990
			BR 8904061 A	27-03-1990
			CA 1337145 C	03-10-1995
			CN 1040811 A	28-03-1990
			DE 68917059 D1	01-09-1994
			DE 68917059 T2	17-11-1994
			DK 394089 A	13-02-1990
			EP 0358338 A2	14-03-1990
			ES 2059772 T3	16-11-1994
			IN 176027 A1	23-12-1995
			JP 2085373 A	26-03-1990
			NO 893250 A	13-02-1990
			PT 91432 A ,B	08-03-1990
			ZA 8905972 A	30-05-1990
US 4330446	A	18-05-1982	JP 1045723 C	28-05-1981
			JP 53092846 A	15-08-1978
			JP 54034406 B	26-10-1979
			JP 1002122 C	19-06-1980
			JP 53121034 A	23-10-1978
			JP 54034783 B	29-10-1979
			JP 1002124 C	19-06-1980
			JP 53123435 A	27-10-1978
			JP 54034784 B	29-10-1979
			JP 989047 C	29-02-1980
			JP 53011989 A	02-02-1978
			JP 54022230 B	04-08-1979
			CA 1090551 A1	02-12-1980
			DE 2732753 A1	26-01-1978
			GB 1562651 A	12-03-1980
EP 0878519	A	18-11-1998	JP 11029724 A	02-02-1999
			AT 248208 T	15-09-2003
			AU 738252 B2	13-09-2001
			AU 6488798 A	19-11-1998
			CA 2237493 A1	14-11-1998
			CN 1201056 A	09-12-1998
			DE 69817442 D1	02-10-2003
			EP 0878519 A1	18-11-1998
			TW 387945 B	21-04-2000
			US 5969019 A	19-10-1999
JP 54077635	A	21-06-1979	JP 1051757 C	26-06-1981
			JP 55041711 B	25-10-1980

EP FORM P0458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.

EP 01 40 0522

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

03-12-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0979880 A	16-02-2000	JP 2001073162 A	21-03-2001
		EP 0979880 A1	16-02-2000
		KR 2000017277 A	25-03-2000
		US 6309477 B1	30-10-2001
-----			